

Test Report

No.: 70.452.22.10629.01

Dated: 2022-04-06



Greater China

Applicant: NANJING HANBU TRAVEL SUPPLIES CO., LTD
Address: 1-58 RUIJIN ROAD, QINHUI DISTRICT, NANJING CITY, JIANGSU PROVINCE, CHINA
Product Name: Shoulder Carrier
Style No.: WIPHA/Camel-1
Supplier: Nanjing Hanbu Travel Supplies Co., Ltd;
Country of Origin: CHINA
Country of Destination: EU
Receipt Date of Sample: 2022-03-10
Date of Testing: 2022-03-10 to 2022-04-06
Sample Submitted: The sample(s) was (were) submitted by applicant and identified.
Test Result: Refer to the data listed in following pages


Test Item

1. EN 13209-2:2015(E)- Migration of certain elements

Conclusion

Pass

Remarks: 1. MDL = Method Detection Limit
2. ND = Not Detected (<MDL)
3. <= Less than
4. 1 mg/kg = 1 ppm = 0.0001%





TÜV SÜD Certification and Testing (China) Co.,Ltd. Shanghai Branch
Testing Center

Prepared by:

Handwritten signature of Jenny Yao in black ink.



Jenny Yao
Technical Engineer

Authorized by:


Handwritten signature of Sawyer Tang in black ink.

Sawyer Tang
Technical Manager

Note:

- (1) The TÜV SÜD Certification and Testing (China) Co., Ltd. "General Terms & Conditions" applied.
Any use for advertising purposes must be granted in writing. This technical report may only be quoted in full. This report is the result of a single examination of the object in question and is not generally applicable evaluation of the quality of other products in regular production.
For further details, please see "Testing and certification regulation", chapter A-3.4
For full version, please visit: EN : <https://www.tuvsud.cn/zh-cn/resource/terms-and-conditions---en> ; SCN: <https://www.tuvsud.cn/zh-cn/terms-and-conditions> ; TCN: <https://www.tuvsud.com/zh-tw/terms-and-conditions>
- (2) The results relate only to the Items tested.
- (3) The test report shall not be reproduced except in full without the written approval of the laboratory
- (4) Disclaimer Measurement Uncertainty:
Unless otherwise agreed upon, Pass or Fail verdicts are given based on the measured values without any considerations of measurement uncertainties.
Please note, every test method has a measurement uncertainty which has been evaluated by the laboratory according to ISO/IEC 17025 requirements. By taking measurement uncertainties into account it might happen that measured values can neither be assessed as Pass nor as Fail.

Description of the Tested Subject

Sample	Description	Photo
001	Shoulder Carrier WIPHA/Camel-1	

T. No	Sample	Description
T1	002	Grey fabric with backing (body)
T2	003	Grey white webbing belt with silvery coating
T3	004	Deep grey plastic (backrest)
T4	005	Grey plastic hook fastener
T5	006	Grey plastic (buckle)
T6	007	Orange red plastic (buckle)
T7	008	Black plastic (joint)
T8	009	Silvery grey plastic (button on joint)
T9	010	Grey elastic band
T10	011	Black elastic band
T11	012	White thread (logo)
T12	013	Grey textile loop fastener
T13	014	Bright silvery grey webbing fabric (binding)
T14	015	Mid grey webbing belt (cover of pole)
T15	016	Bright silvery grey webbing belt (adjuster belt)
T16	017	Orange red webbing belt
T17	018	Grey thick mesh fabric
T18	019	Grey thick big mesh fabric (back)



Test Results

1. EN 13209-2:2015(E)- Migration of certain elements

Test with reference to EN 71-3:2013+A1:2014,determination by ICP-MS.

Test Item	Limit in scraped-off toy materials [mg/kg]	MDL [mg/kg]	Result(s) [mg/kg]					
			002	003	004	005	006	007
Soluble Aluminum	70000	5.00	7.60	8.30	10.3	8.44	6.50	<5.00
Soluble Antimony	560	5.00	<5.00	<5.00	<5.00	<5.00	<5.00	<5.00
Soluble Arsenic	47	5.00	<5.00	<5.00	<5.00	<5.00	<5.00	<5.00
Soluble Barium	18750	5.00	<5.00	<5.00	<5.00	<5.00	<5.00	<5.00
Soluble Boron	15000	5.00	<5.00	<5.00	<5.00	<5.00	<5.00	<5.00
Soluble Cadmium	17	5.00	<5.00	<5.00	<5.00	<5.00	<5.00	<5.00
Soluble Chromium III	460	0.04	<0.04	0.553	0.227	0.176	0.105	<0.04
Soluble Chromium VI	0.2	0.04	<0.04	<0.04	<0.04	<0.04	<0.04	<0.04
Soluble Cobalt	130	5.00	<5.00	<5.00	<5.00	<5.00	<5.00	<5.00
Soluble Copper	7700	5.00	<5.00	<5.00	<5.00	<5.00	<5.00	<5.00
Soluble Lead	160	5.00	<5.00	<5.00	<5.00	<5.00	<5.00	<5.00
Soluble Manganese	15000	5.00	<5.00	<5.00	<5.00	<5.00	<5.00	<5.00
Soluble Mercury	94	5.00	<5.00	<5.00	<5.00	<5.00	<5.00	<5.00
Soluble Nickel	930	5.00	<5.00	<5.00	<5.00	<5.00	<5.00	<5.00
Soluble Selenium	460	5.00	<5.00	<5.00	<5.00	<5.00	<5.00	<5.00
Soluble Strontium	56000	5.00	<5.00	<5.00	<5.00	<5.00	<5.00	<5.00
Soluble Tin	180000	2.50	<2.50	<2.50	<2.50	<2.50	<2.50	<2.50
Organic Tin	12	7.50	<7.50	<7.50	<7.50	<7.50	<7.50	<7.50
Soluble Zinc	46000	5.00	<5.00	<5.00	<5.00	<5.00	<5.00	<5.00
Conclusion			Pass	Pass	Pass	Pass	Pass	Pass



Test Item	Limit in scraped-off toy materials [mg/kg]	MDL [mg/kg]	Result(s) [mg/kg]					
			008	009	010	011	012	013
Soluble Aluminum	70000	5.00	<5.00	6.25	7.55	7.20	15.4	15.1
Soluble Antimony	560	5.00	<5.00	<5.00	<5.00	<5.00	<5.00	<5.00
Soluble Arsenic	47	5.00	<5.00	<5.00	<5.00	<5.00	<5.00	<5.00
Soluble Barium	18750	5.00	<5.00	<5.00	<5.00	<5.00	<5.00	<5.00
Soluble Boron	15000	5.00	<5.00	<5.00	<5.00	<5.00	<5.00	<5.00
Soluble Cadmium	17	5.00	<5.00	<5.00	<5.00	<5.00	<5.00	<5.00
Soluble Chromium III	460	0.04	0.115	<0.04	0.550	<0.04	0.704	0.190
Soluble Chromium VI	0.2	0.04	<0.04	<0.04	<0.04	<0.04	<0.04	<0.04
Soluble Cobalt	130	5.00	<5.00	<5.00	<5.00	<5.00	<5.00	<5.00
Soluble Copper	7700	5.00	<5.00	<5.00	<5.00	<5.00	<5.00	<5.00
Soluble Lead	160	5.00	<5.00	<5.00	<5.00	<5.00	<5.00	<5.00
Soluble Manganese	15000	5.00	<5.00	<5.00	<5.00	<5.00	<5.00	<5.00
Soluble Mercury	94	5.00	<5.00	<5.00	<5.00	<5.00	<5.00	<5.00
Soluble Nickel	930	5.00	<5.00	<5.00	<5.00	<5.00	<5.00	<5.00
Soluble Selenium	460	5.00	<5.00	<5.00	<5.00	<5.00	<5.00	<5.00
Soluble Strontium	56000	5.00	<5.00	<5.00	<5.00	<5.00	<5.00	<5.00
Soluble Tin	180000	2.50	<2.50	<2.50	<2.50	<2.50	<2.50	<2.50
Organic Tin	12	7.50	<7.50	<7.50	<7.50	<7.50	<7.50	<7.50
Soluble Zinc	46000	5.00	<5.00	<5.00	<5.00	290	7.99	<5.00
Conclusion			Pass	Pass	Pass	Pass	Pass	Pass



Test Item	Limit in scraped-off toy materials [mg/kg]	MDL [mg/kg]	Result(s) [mg/kg]					
			014	015	016	017	018	019
Soluble Aluminum	70000	5.00	13.8	7.55	10.6	5.83	<5.00	<5.00
Soluble Antimony	560	5.00	<5.00	<5.00	<5.00	<5.00	<5.00	<5.00
Soluble Arsenic	47	5.00	<5.00	<5.00	<5.00	<5.00	<5.00	<5.00
Soluble Barium	18750	5.00	<5.00	<5.00	<5.00	<5.00	<5.00	<5.00
Soluble Boron	15000	5.00	<5.00	<5.00	<5.00	<5.00	<5.00	<5.00
Soluble Cadmium	17	5.00	<5.00	<5.00	<5.00	<5.00	<5.00	<5.00
Soluble Chromium III	460	0.04	0.800	0.650	0.377	0.211	<0.04	<0.04
Soluble Chromium VI	0.2	0.04	<0.04	<0.04	<0.04	<0.04	<0.04	<0.04
Soluble Cobalt	130	5.00	<5.00	<5.00	<5.00	<5.00	<5.00	<5.00
Soluble Copper	7700	5.00	<5.00	<5.00	<5.00	<5.00	<5.00	<5.00
Soluble Lead	160	5.00	<5.00	<5.00	<5.00	<5.00	<5.00	<5.00
Soluble Manganese	15000	5.00	<5.00	<5.00	<5.00	<5.00	<5.00	<5.00
Soluble Mercury	94	5.00	<5.00	<5.00	<5.00	<5.00	<5.00	<5.00
Soluble Nickel	930	5.00	<5.00	<5.00	<5.00	<5.00	<5.00	<5.00
Soluble Selenium	460	5.00	<5.00	<5.00	<5.00	<5.00	<5.00	<5.00
Soluble Strontium	56000	5.00	<5.00	<5.00	<5.00	<5.00	<5.00	<5.00
Soluble Tin	180000	2.50	<2.50	<2.50	<2.50	<2.50	<2.50	<2.50
Organic Tin	12	7.50	<7.50	<7.50	<7.50	<7.50	<7.50	<7.50
Soluble Zinc	46000	5.00	5.55	<5.00	<5.00	<5.00	<5.00	<5.00
Conclusion			Pass	Pass	Pass	Pass	Pass	Pass

- End of Test Report -